

ACI 211.7R-15

Guide for Proportioning Concrete Mixtures with Ground Limestone and Other Mineral Fillers

Reported by ACI Committee 211



American Concrete Institute
Always advancing



Guide for Proportioning Concrete Mixtures with Ground Limestone and Other Mineral Fillers

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

Guide for Proportioning Concrete Mixtures with Ground Limestone and Other Mineral Fillers

Reported by ACI Committee 211

Gary F. Knight, Chair
Timothy S. Folks, Vice Chair

Ed T. McGuire, Secretary

William L. Barringer
Katie J. Bartojay
Muhammed P. A. Basheer
James C. Blankenship
Casimir J. Bognacki
Michael J. Boyle
Ramon L. Carrasquillo
Bryan R. Castles
Teck L. Chua
James E. Cook
John F. Cook
David A. Crocker
D. Gene Daniel
Kirk K. Deadrick
Donald E. Dixon
Darrell F. Elliot

David W. Fowler
G. Terry Harris
Richard D. Hill
David L. Hollingsworth
Said Iravani
Tarif M. Jaber
Robert S. Jenkins
Joe Kelley
Eric P. Koehler
Frank A. Kozeliski
Darmawan Ludirdja
Allyn C. Luke
Kevin A. MacDonald
Gary R. Mass
Warren E. McPherson Jr.
Jon I. Mullarky

Karthik H. Obla
H. Celik Ozyildirim
James S. Pierce
Steven A. Ragan
Royce J. Rhoads
John P. Ries
G. Michael Robinson
James M. Shilstone Jr.
Ava Shypula
Woodward L. Vogt
Michael A. Whisonant

Kenneth W. Day
Timothy S. Folks
Plinio Estuardo Herrera
Kenneth G. Kazanis
Guy Lortie
Nicholas J. Popoff
Lane G. Shaw
Lawrence L. Sutter
Caroline M. Talbot
Paul D. Tennis
Paul J. Thomas
John W. Vaughan
Hermann W. Wentz

Subcommittee Members

David Anstine
Dale P. Bentz
Joseph A. Daczko

Consulting Member
James N. Lingscheit

The use of ground limestone and other mineral fillers can enhance the performance, economy, and sustainability of concrete mixtures. Modifications to the conventional proportioning method in ACI 211.1 are needed to incorporate these materials. This document describes ground limestone and other mineral fillers, including their properties, characterization, and qualification, and effects on concrete properties and sustainability. Recommendations are provided for proportioning concrete mixtures with these materials.

Keywords: dust-of-fracture; ground limestone; mineral fillers; mixture proportioning; paste volume; powder content; proportioning.

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

CONTENTS

CHAPTER 1—INTRODUCTION, p. 2

CHAPTER 2—DEFINITIONS, p. 2

CHAPTER 3—CONSTITUENT MATERIALS, p. 2

3.1—Introduction, p. 2

3.2—Ground limestone, p. 3

3.3—Dust-of-fracture mineral filler, p. 3

CHAPTER 4—GROUND LIMESTONE AND MINERAL FILLER CHARACTERIZATION AND QUALIFICATION, p. 3

4.1—Introduction, p. 3

4.2—Morphology (shape, angularity, and texture), p. 3

4.3—Mineralogy, p. 3

4.4—Particle size and particle size distribution, p. 3

4.5—Deleterious materials, p. 4

ACI 211.7R-15 was adopted and published May 2015.

Copyright © 2015, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

4.6—Relative density (specific gravity), p. 4

CHAPTER 5—EFFECTS ON CONCRETE PROPERTIES, p. 4

- 5.1—Rheology and workability, p. 4
- 5.2—Placement and finishing characteristics, p. 5
- 5.3—Strength, p. 5
- 5.4—Setting time, p. 6
- 5.5—Durability, p. 6

CHAPTER 6—PROPORTIONING METHODS, p. 7

- 6.1—Basic relationships, p. 7
- 6.2—Modified ACI 211.1 method for ground limestone, p. 8
- 6.3—Modified ACI 211.1 method for dust-of-fracture mineral fillers, p. 9

CHAPTER 7—SAMPLE COMPUTATIONS, p. 10

- 7.1—Wet mineral filler in manufactured sand, p. 10
- 7.2—Dry mineral filler, p. 11
- 7.3—Adjustment of trial batches, p. 12

CHAPTER 8—SUSTAINABILITY, p. 12

- 8.1—Ground limestone, p. 12
- 8.2—Dust-of-fracture mineral fillers, p. 12

CHAPTER 9—REFERENCES, p. 13

CHAPTER 1—INTRODUCTION

This guide provides recommendations for proportioning normalweight concrete with ground limestone and dust-of-fracture mineral fillers. It is intended to supplement ACI 211.1. Proportioning methods for ground limestone and for dust-of-fracture mineral filler are discussed separately.

Mineral filler is defined as a finely divided mineral product at least 65 percent of which passes the No. 200 (75 μm) sieve. Ground limestone is a purposefully manufactured fine product composed primarily of calcium carbonate and with particles sized within narrow ranges. Ground limestone has been used successfully in concrete in Europe for decades, either added to the concrete mixture separately from the cement or interground with clinker to form portland-limestone cement.

Dust-of-fracture mineral filler is rock dust created during production, processing, or handling of quarried stone. Such materials are not purposefully manufactured and can vary in mineral composition and other physical characteristics, depending on the parent stone from which they are derived, the crushing process, and the washing or air separation process.

This guide does not address precipitated calcium carbonate or material finer than the No. 200 (75 μm) sieve in natural sand. Although ground limestone typically falls within the definition of mineral filler, it is dealt with separately in this guide from other mineral fillers. It is manufactured under controlled conditions to be a consistent product. Dust-of-fracture mineral filler consisting primarily of calcium carbonate is not considered ground limestone.

The aggregate suspension mixture proportioning method described in ACI 211.6T has been used to proportion concrete with ground limestone and dust-of-fracture mineral filler.

Concrete mixture proportioning is becoming more critical with changing government regulations and policies for sustainable development in the construction industry. Ground limestone has a lower embodied energy and lower CO₂ emission during its production than an equivalent mass of portland cement. This guide can facilitate the use of ground limestone and other mineral fillers as a means of optimizing the cementitious materials content of concrete, thereby increasing sustainability.

Applicability of these materials is not limited to a select class or type of concrete but can be considered for use in a wide variety of applications and production methods. The described proportioning methods provide a first approximation of proportions intended for trial batches in the laboratory or field, which should be adjusted as necessary to produce the desired characteristics of the concrete.

Ground limestone and dust-of-fracture mineral filler can also be used in structural lightweight concrete. The principles described herein can be similarly used to modify ACI 211.2 to incorporate these materials.

CHAPTER 2—DEFINITIONS

ACI provides a comprehensive list of definitions through an online resource, “ACI Concrete Terminology,” <http://www.concrete.org/tools/concreteterminology.aspx>. Definitions provided herein complement that source.

ground limestone—material with specified amount of calcium carbonate and produced by milling the rock to a specific particle size distribution.

paste volume—volume of cementitious materials and other powders, water, and chemical admixtures.

powder—solid materials finer than approximately 75 μm including cement, supplementary cementitious materials, and the portion of fine aggregate, ground limestone, and other mineral fillers finer than 75 μm .

water-powder ratio—ratio of the mass of water, excluding that absorbed by the aggregate, to the mass of powder in a mixture, stated as a decimal and abbreviated *w/p*.

CHAPTER 3—CONSTITUENT MATERIALS

3.1—Introduction

The selection of constituent materials when proportioning concrete with ground limestone or dust-of-fracture mineral filler is very similar to the typical selection process described in ACI 211.1. Mixture constituents such as coarse and fine aggregate (ACI 221R), cementitious materials (ACI 225R; ACI 232.2R; ACI 233R; ACI 234R), admixtures (ACI 212.3R), and water that are commonly used for proportioning concrete are usually suitable when proportioning with ground limestone and dust-of-fracture mineral filler. The most significant adjustments to proportions will be in amount of water used, the type and dosage of admixtures, and minor changes to coarse and fine aggregate ratios.