

**Guide to Evaluation of
Strength Test Results of Concrete**

Reported by ACI Committee 214



American Concrete Institute®



First Printing
April 2011

American Concrete Institute®
Advancing concrete knowledge

Guide to Evaluation of Strength Test Results of Concrete

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at www.concrete.org/committees/errata.asp. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised *ACI Manual of Concrete Practice* (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
U.S.A.

Phone: 248-848-3700
Fax: 248-848-3701

www.concrete.org

ISBN 978-0-87031-423-0

Guide to Evaluation of Strength Test Results of Concrete

Reported by ACI Committee 214

Casimir Bognacki*
Chair

Jerry Parnes
Secretary

David J. Ackers
Madasamy Arockiasamy

William L. Barringer

F. Michael Bartlett*

Jerrold L. Brown

Bryan R. Castles*

James E. Cook

Ronald L. Dilly

Donald E. Dixon

Richard D. Gaynor

Alejandro Graf

Thomas M. Greene

Gilbert J. Haddad

Kal R. Hindo

Robert S. Jenkins

Alfred L. Kaufman Jr.

William F. Kepler

Michael L. Leming

Colin L. Lobo*

John J. Luciano

Allyn C. Luke*

Stephen S. Marchese

Richard E. Miller

Venkataswamy Ramakrishnan

D. V. Reddy

David N. Richardson*

James M. Shilstone Jr.

Bryce P. Simons

Luke M. Snell

Patrick J. E. Sullivan

Eugene Takhtovich*

Michael A. Taylor

Roger E. Vaughan

Woodward L. Vogt*

Orville R. Werner II

*Committee members who prepared this guide.

Statistical procedures provide valuable tools for evaluating the results of concrete strength tests. Information derived from such procedures is valuable in defining design criteria, specifications, and other parameters needed for structural evaluation and repair. This guide discusses variations that occur in concrete strength and presents statistical procedures useful in interpreting these variations with respect to specified testing and criteria.

Keywords: coefficient of variation; concrete strength; normal distribution; required overdesign; quality control; standard deviation; statistical methods.

ACI Committee Reports, Guides, Manuals, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

CONTENTS

Chapter 1—Introduction, p. 2

1.1—Introduction

1.2—Summary

Chapter 2—Notation and definitions, p. 2

2.1—Notation

2.2—Definitions

Chapter 3—Variations in strength, p. 3

3.1—General

3.2—Influence of batch-to-batch variations on concrete strength

3.3—Influence of within-batch variations on concrete strength

ACI 214R-11 supersedes 214R-02 and was adopted and published April 2011.
Copyright © 2011, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

Chapter 4—Analysis of strength data, p. 4

- 4.1—General
- 4.2—Statistical functions
- 4.3—Strength variations
- 4.4—Interpretation of statistical parameters
- 4.5—Standards of control

Chapter 5—Criteria, p. 8

- 5.1—General
- 5.2—Data used to establish minimum required average strength
- 5.3—Criteria for strength requirements

Chapter 6—Evaluation of data, p. 11

- 6.1—General
- 6.2—Numbers of tests
- 6.3—Rejection of doubtful specimens
- 6.4—Additional test requirements
- 6.5—Quality-control charts
- 6.6—Additional evaluation techniques

Chapter 7—References, p. 16

- 7.1—Referenced standards and reports
- 7.2—Cited references

CHAPTER 1—INTRODUCTION**1.1—Introduction**

This guide provides an introduction to the evaluation of concrete strength test results. Procedures described are applicable to the compressive strength test results required by ACI 301, ACI 318, and similar specifications and codes. Statistical concepts described are applicable for the analysis of other common concrete test results, including flexural strength, slump, air content, density, modulus of elasticity, and other tests used for evaluating concrete and ingredient materials. This guide assumes that the concrete test results conform to a normal distribution.

Most construction projects in the United States and Canada require routine sampling of concrete and fabrication of standard molded cylinders. These cylinders are usually cast from a concrete sample taken from the discharge of a truck or a batch of concrete. They are molded and cured following the standard procedures of ASTM C31/C31M and tested as required by ASTM C39/C39M. If the concrete is so prepared, cured, and tested, the results are the compressive strength of the concrete cured under controlled conditions, not the in-place strength of the concrete within the structure. It is expected that, given the uniformity of the curing conditions, these cylinders would have essentially the same strength, thereby indicating concrete with consistent properties. It is these cylinders that are used for acceptance purposes.

Inevitably, strength test results vary. Variations in the measured strength of concrete originate from two sources:

- Batch-to-batch variations can result from changes to the ingredients or proportions of ingredients, water-cementitious material ratio (w/cm), mixing, transporting, placing, sampling of the batch, consolidating, and curing; and
- Within-batch variations, also called within-test variations, are primarily due to differences in sampling of the

batch sample, specimen preparation, curing, and testing procedures.

There are differences in individual mixer batches between the front and rear of the mixer, as recognized by ASTM C94/C94M. For this reason, ACI Field Level I Technicians are trained to make composite samples from the central portions of loads.

Conclusions regarding concrete compressive strength can be derived from a series of tests. The characteristics of concrete strength can be accurately estimated when an adequate number of tests are conducted in accordance with standard practices and test methods.

Statistical procedures provide valuable tools when evaluating strength test results. Information derived from them is also valuable in refining design criteria and specifications. This guide discusses variations in concrete strength and presents statistical procedures useful for interpreting them with respect to specified testing and acceptance criteria.

For the statistical procedures described in this guide to be valid, data should be derived from samples obtained through a random sampling plan. Random sampling is when each volume of concrete has an equal chance of being selected. To ensure this condition, selection should be made by using an objective mechanism, such as a table of random numbers. When sample batches are selected on the basis of the sampler's judgment, biases are likely to be introduced that will invalidate the analysis. Natrella (1963), Box et al. (2005), and ASTM D3665 discuss the need for random sampling, and provide a useful short table of random numbers.

1.2—Summary

This guide begins with a discussion in Chapter 3 of the batch-to-batch sources of variability in concrete production, followed by the within-batch sources of variability. Chapter 4 presents the statistical tools that are used to analyze and evaluate concrete variability and determine compliance with a given specification. Chapters 5 and 6 review statistically-based specifications.

CHAPTER 2—NOTATION AND DEFINITIONS**2.1—Notation**

- d_2 = factor for computing within-batch standard deviation from average range (Table 4.1)
- f'_c = specified compressive strength of concrete, psi (MPa)
- f'_{cr} = required average compressive strength of concrete (to ensure that no more than a permissible proportion of tests will fall below the specified compressive strength) used as the basis for selection of concrete proportions, psi (MPa)
- M = the median of a distribution, that is, half the values above and half the values below
- n = number of tests in a record
- R = within-batch range
- \bar{R} = average range
- \bar{R}_m = maximum average range, used in certain control charts