

# **Guide to Design and Construction Practices to Mitigate Corrosion of Reinforcement in Concrete Structures**

Reported by ACI Committee 222



**American Concrete Institute®**



American Concrete Institute®  
Advancing concrete knowledge

First Printing  
April 2011

## Guide to Design and Construction Practices to Mitigate Corrosion of Reinforcement in Concrete Structures

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at [www.concrete.org/committees/errata.asp](http://www.concrete.org/committees/errata.asp). Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided "as is" without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

**Order information:** ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised *ACI Manual of Concrete Practice* (MCP).

**American Concrete Institute**  
**38800 Country Club Drive**  
**Farmington Hills, MI 48331**  
**U.S.A.**

**Phone:**      **248-848-3700**  
**Fax:**        **248-848-3701**

**[www.concrete.org](http://www.concrete.org)**

# Guide to Design and Construction Practices to Mitigate Corrosion of Reinforcement in Concrete Structures

Reported by ACI Committee 222

Mohammad S. Khan  
Chair

David Trejo  
Secretary

Antonio J. Aldykiewicz Jr.

Michael C. Brown  
David Darwin  
Marwan A. Daye  
Stephen D. Disch  
Hamid Farzam  
Per Fidjestøl

David P. Gustafson

Carolyn M. Hansson  
William G. Hime  
Brian B. Hope  
Tracy D. Marcotte  
David B. McDonald  
Theodore L. Neff

Charles K. Nmai

Randall W. Poston  
Ruben M. Salas  
Arpad Savoly  
Andrea J. Schokker  
Morris Schupack  
Khaled A. Soudki

Paul G. Turney  
Yash Paul Virmani  
Jeffrey S. West  
Richard E. Weyers  
David W. Whitmore  
John B. Wojakowski

*Corrosion of metals in concrete is a significant problem throughout the world. In many instances, corrosion can be avoided if proper attention is given to detailing, concrete materials and mixture proportions, and construction practices. This guide contains information on aspects of each of these. In addition, the guide contains recommendations for protecting in-service structures exposed to corrosive conditions. The guide is intended for designers, materials suppliers, contractors, and all others engaged in concrete construction.*

**Keywords:** admixtures; aggregates; aluminum; cathodic protection; cement; chlorides; consolidation; corrosion; curing; epoxy coating; high-range water-reducing admixtures; mixing; mixture proportioning; permeability; reinforcing steel; water-cementitious material ratio.

ACI Committee Reports, Guides, Manuals, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

## CONTENTS

### **Foreword, p. 2**

### **Chapter 1—Introduction, p. 2**

### **Chapter 2—Design considerations, p. 2**

- 2.1—Structural types and corrosion
- 2.2—Environment and corrosion
- 2.3—Cracking and corrosion
- 2.4—Structural details and corrosion

### **Chapter 3—Impact of mixture proportioning, concreting materials, and type of embedded metal, p. 7**

- 3.1—Influence of mixture proportioning on corrosion of reinforcing steel
- 3.2—Influence of selection of cement, aggregates, water, and admixtures on corrosion of reinforcing steel
- 3.3—Uncoated reinforcing steel
- 3.4—Epoxy-coated reinforcing steel
- 3.5—Embedded metals other than reinforcing steel

ACI 222.3R-11 supersedes 222.3R-03 and was adopted and published April 2011.  
Copyright © 2011, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

**Chapter 4—Construction practices, p. 13**

- 4.1—Mixing and transporting concrete
- 4.2—Placement of concrete and steel
- 4.3—Consolidation
- 4.4—Influence of curing on corrosion of reinforcing steel

**Chapter 5—Evaluation and protection of in-service structures, p. 15**

- 5.1—Types of structures susceptible to corrosion-related deterioration
- 5.2—Evaluation of in-service structures
- 5.3—Barrier systems for concrete
- 5.4—Admixtures that extend life of reinforced concrete structures exposed to chloride environments
- 5.5—Cathodic protection
- 5.6—Electrochemical chloride extraction

**Chapter 6—References, p. 20**

- 6.1—Referenced standards and reports
- 6.2—Cited references

**FOREWORD**

This guide represents a compendium of technology to combat the problems of corrosion and is arranged into four major chapters. Chapter 2 discusses design considerations pertinent to corrosion, including environmental factors, performance of structural types, and the influence of structural details. Chapter 3 addresses the effects of concrete materials and mixture proportions on susceptibility to corrosion, including cements, aggregates, water, reinforcing steels, admixtures, and other embedded materials. Chapter 4 examines corrosion as it is influenced by the changes that concrete undergoes as it is mixed, transported, placed, consolidated, and cured. Chapter 5 describes several procedures available for protecting in-place structures.

This guide will aid in the design and construction of corrosion-resistant reinforced concrete structures and assist those involved in ensuring that reinforced concrete continues to function as a reliable and durable construction material.

**CHAPTER 1—INTRODUCTION**

Corrosion of metals in concrete is a serious type of deterioration that affects concrete in service. Corrosion is seen in parking structures, marine structures, industrial plants, buildings, bridges, and pavements. The Federal Highway Administration published a report in 2001 that the estimated cost of corrosion of highway bridges was between \$6.43 and \$10.15 billion (FWHA-RD-01-097 2001). This problem drains resources in both the public and private sectors. Implementation of solutions is needed, both in the design of structures resistant to corrosion and the rehabilitation of structures suffering the effects of corrosion.

Concrete provides a highly alkaline environment, which results in the formation of a passivating film that protects the steel from corrosion. Corrosion of embedded metals in concrete can occur, however, if concrete quality and details such as concrete cover and crack control are not adequate; if the functional requirement of the structure is not as anticipated or is not adequately addressed in the design; if the environment

is not as anticipated or changes during the service life of the structure; or a combination of thereof. For more details on the mechanism of corrosion of metals in concrete, refer to ACI 222R.

Once corrosion begins, it is aggravated by factors such as moisture and elevated ambient temperatures. Cracking, stray currents, and galvanic effects can also exacerbate corrosion. Other causes of corrosion include steel directly exposed to the corrosive elements due to incomplete placement or consolidation of concrete, and industrial or wastewater chemicals that attack the concrete and the reinforcing steel. Reinforced concrete structures should be designed either to avoid these factors when they are present or be protected from these factors when they cannot be avoided.

**CHAPTER 2—DESIGN CONSIDERATIONS****2.1—Structural types and corrosion**

Corrosion of steel in concrete was first observed in marine structures and chemical manufacturing plants (Biczok 1964; Evans 1960; Tremper et al. 1958). The design considerations relevant to corrosion protection depend on the type of structure and its environment and intended use. Certain minimum measures—for example, adequate concrete cover and concrete quality—should always be specified, even for structures such as concrete office buildings completely enclosed in a curtain wall with no exposed structural elements. Depending on the type of structure and its expected exposure, additional design considerations can be required to ensure satisfactory performance over the intended service life of the structure.

**2.1.1 Bridges**—The primary issues in designing the deck, substructure, and superstructure of a concrete bridge for increased corrosion resistance are knowing the potential for chloride ion exposure while in service and the degree of protection required. In theory, the design considerations for a bridge located in a semi-arid region of the U.S., such as parts of Arizona, should be different from a bridge located in either Illinois or on the coast of Florida. ACI 318, ACI 345R, and AASHTO HB-17 recognize this and contain additional requirements for concrete structures exposed to different levels of chloride ions in service.

There are differences in interpretation when applying these provisions for corrosion protection of bridge structures. For exposure to deicing chemicals, the top mat of reinforcement is more susceptible to chloride-induced corrosion than the bottom mat and, therefore, acts as the anode with the bottom mat acting as the cathode in macrocell corrosion. AASHTO HB-17 recognizes this and requires greater concrete cover for the top mat of reinforcement. This basic premise of chloride-ion exposure is reversed for a bridge located in a warm climatic area over saltwater where the underside of the bridge deck can be more vulnerable to chloride-ion ingress. Consequently, the concrete cover should be increased for the bottom mat of deck reinforcement in this type of application.

So much has been written about the bridge deck problem since the early 1970s that corrosion protection of a bridge superstructure and substructure has sometimes been overlooked. Leakage of chloride-contaminated water through expansion and construction joints and cracks onto the superstructure,