

ACI 304.2R-17

Guide to Placing Concrete by Pumping Methods

Reported by ACI Committee 304



American Concrete Institute
Always advancing



Guide to Placing Concrete by Pumping Methods

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Guide to Placing Concrete by Pumping Methods

Reported by ACI Committee 304

Larry G. Leper, Chair

Hakim S. Abdelgader
David J. Akers
Casimir J. Bognacki
David A. Burg
Manjit S. Chopra
Bernard J. Eckholdt III
J. Mitchell Engelstead

Michael R. Gardner
Daniel J. Green
Neil R. Guptill
Terence C. Holland
Tarek S. Khan
Gary R. Mass
Larry W. Matejcek

Avi A. Mor
Mike Murray
Dipak T. Parekh
James S. Pierce
Jorge L. Quiros Jr.
Royce J. Rhoads
James M. Shilstone Jr.

Boris Y. Stein
Samuel X. Yao
Richard Yelton

Consulting Member
Thomas R. Clapp

The committee would like to give special acknowledgement to associate member J. Bury, Chair of the subcommittee that prepared this document, for his considerable contribution to its development.

This guide discusses the use of pumps for transporting and placing concrete. Rigid and flexible pipelines, couplings and other accessories, and the various types of concrete pumps are discussed. The importance of proportioning a pumpable concrete mixture is emphasized with reference to sources for further direction on its design. Evaluation of trial mixtures to ensure pumpability and strength is encouraged. Of specific importance is a discussion on the use of lightweight aggregates. Methods to saturate these aggregates and provide a consistent moisture content are discussed.

Preconstruction planning for equipment placement and line routing are emphasized. Discussions on achieving a consistent mixture and its critical importance are also addressed.

Keywords: blockage; boundary layer; concrete pump; coupling; mixture design; pipeline; placing boom; preprimed; pumpability; reverse pumping; valve.

CONTENTS

CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

- 1.1—Introduction, p. 2
- 1.2—Scope, p. 2

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

CHAPTER 2—DEFINITIONS, p. 2

CHAPTER 3—PUMPING CONCRETE, p. 2

- 3.1—Mixture component distribution, p. 2
- 3.2—Disruptions to flow, p. 3

CHAPTER 4—PUMPING EQUIPMENT AND COMPONENTS, p. 4

- 4.1—Piston pumps, p. 4
- 4.2—Valve types, p. 4
- 4.3—Trailer pumps, p. 5
- 4.4—Truck-mounted concrete pumps, p. 5
- 4.5—Separate placing booms, p. 6
- 4.6—Specialized equipment, p. 6
- 4.7—Pipeline and accessories, p. 6
- 4.8—Flexible system hose types and applications, p. 9
- 4.9—Concrete placing system accessories, p. 9

CHAPTER 5—PUMPABLE CONCRETE, p. 11

- 5.1—Basic considerations, p. 11
- 5.2—Normalweight aggregate, p. 11
- 5.3—Lightweight aggregate concrete, p. 12
- 5.4—Water and slump, p. 12
- 5.5—Cementitious materials, p. 14
- 5.6—Admixtures, p. 14
- 5.7—Fiber reinforcement, p. 14
- 5.8—Trial mixtures and pumpability testing, p. 15
- 5.9—Estimating performance, p. 15

ACI 304.2R-17 supersedes ACI 304.2R-96 and was adopted and published October 2017.

Copyright © 2017, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 6—FIELD PRACTICES, p. 15

- 6.1—General, p. 15
- 6.2—Pipeline concrete placement, p. 16
- 6.3—Powered boom placement, p. 17
- 6.4—Equipment and operational safety, p. 18
- 6.5—Reduction in air content, p. 18

CHAPTER 7—FIELD CONTROL, p. 19**CHAPTER 8—REFERENCES, p. 19**

Authored documents, p. 19

CHAPTER 1—INTRODUCTION AND SCOPE**1.1—Introduction**

Pumping concrete through metal pipelines by piston pumps was introduced to the United States in Milwaukee, WI, in 1933 (Ball 1933). This concrete pump used mechanical linkages to operate, and usually pumped through pipelines 6 in. (150 mm) or larger in diameter.

Many new developments have since been made in the concrete pumping field. These include new and improved pumps, truck-mounted and stationary placing booms, and pipelines and hoses that withstand higher pumping pressures. Pumps are available with maximum theoretical output capacities of over 250 yd³/h (190 m³/h). As a result of these innovations, concrete placement by pumps has become one of the most widely used practices of the construction industry.

The construction industry recognizes that concrete pumping is useful when space for construction equipment is limited. Cranes and hoists are freed up and other crafts can work unhampered while pumping is in progress. Concrete pumps are designed to deliver the best combination of volume output and concrete line pressure possible.

How well the pump performs in an application depends on many factors, both internal and external to the equipment itself—for example, ambient temperature influences pump performance. Pipe diameter, pumping direction both for vertical and horizontal distance, and concrete mixture characteristics also have an effect.

As construction designs and projects become more sophisticated, such as requiring higher strength and greater durability, concrete mixture design today is more complex than what was traditionally placed (Putzmeister America, Inc 2010; American Concrete Pumping Association 2007, 2010, 2011b).

Pumpability is one consideration the contractor can request from the designer when specifying mixtures. Engineered mixtures, using special materials and processing, must consider design details including final strength, curing characteristics, site conditions such as underwater placement, material and handling expenses, flow characteristics, delivery/placement, and sustainability impacts. In cases where these features are in direct conflict, a compromise or alternate solution is necessary. Given the popularity and benefits of placement by pumping, it could become critical to a specific application that the components and proportions of a mixture be designed with consideration of pumpability.

There are many variables that could affect the successful pumping of a mixture in an application, including the specific requirements of a specific combination of materials, equipment components, and installation circumstances, of which several will be discussed in more detail in this guide.

This guide discusses concrete placement using the pumping method and how it affects the supplied concrete mixture when considering pumpability in mixture design, and with the goal to obtain optimum concrete pumping results.

1.2—Scope

This guide for concrete pumping discusses equipment use, proper mixtures for good pumpability, and field practices. References cited provide more detailed information on specific subjects. This guide does not address shotcreting or pumping of nonstructural insulating or cellular concrete.

CHAPTER 2—DEFINITIONS

ACI provides a comprehensive list of definitions through an online resource, “ACI Concrete Terminology”, <https://www.concrete.org/store/productdetail.aspx?ItemID=CT13>. Definitions provided herein complement that source.

boundary layer—thin coating of mortar fraction that lines the inner pipeline wall during pumping.

degree of pumpability—the amount of resistance of a specific concrete mixture to being pumped through a delivery pipeline.

pumpability—capability of a specific concrete mixture to being pumped through a delivery pipeline.

relative movement—ability of concrete components to navigate small distances within the mixture and to position differently compared to the other components.

stable concrete—concrete mixture that resists the tendency to segregate.

CHAPTER 3—PUMPING CONCRETE

Pumped concrete moves as a cylinder riding on a thin lubricating film of grout or mortar on the inside diameter of the pipeline. Before pumping begins, the entire pipeline’s interior diameter must be coated with either grout or a specialized commercial primer using the methods for 100 percent coating of the pipe walls as recommended by the manufacturer. Once concrete flow through the pipeline is established, the lubrication will be maintained as long as pumping continues with a properly proportioned and consistent mixture. A steady supply of pumpable concrete, defined as a mixture that is capable of being pumped through a hose or pipe, is necessary for satisfactory pumping (U.S. Bureau of Reclamation 1981). A pumpable concrete, such as conventional concrete, requires good quality control; that is, it is uniform, has properly graded aggregate, and its materials are uniformly batched and mixed thoroughly.

3.1—Mixture component distribution

3.1.1 Boundary layer—From the concrete pump’s delivery cylinder to the point-of-placement end hose, effective and efficient concrete pumping depends on minimizing any