

IN-LB

Inch-Pound Units

SI

International System of Units

An ACI Standard

Commercial Concrete Parking Lots and Site Paving Design and Construction—Guide

Reported by ACI Committee 330

ACI PRC-330-21



American Concrete Institute
Always advancing



Commercial Concrete Parking Lots and Site Paving Design and Construction—Guide

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint, and may be obtained by contacting ACI.

ACI codes, specifications, and practices are made available in the ACI Collection of Concrete Codes, Specifications, and Practices. The online subscription to the ACI Collection is always updated, and includes current and historical versions of ACI’s codes and specifications (in both inch-pound and SI units) plus new titles as they are published. The ACI Collection is also available as an eight-volume set of books and a USB drive.

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

Commercial Concrete Parking Lots and Site Paving Design and Construction—Guide

Reported by ACI Committee 330

Christopher R. Tull, Chair

Jason D. Wimberly, Secretary

Richard O. Albright
Daniel T. Biddle
Bryan M. Birdwell
Jacob L. Borgerson
David W. Buzzelli
Michael W. Cook
Tim Cost

Anthony R. DeCarlo
Norbert J. Delatte
Bruce A. Glaspey
R. Scott Haislip
Myron J. Hillock
Amanda H. Hult
Frank A. Kozeliski

Jesse L. Long
Steven L. Mallicoat
Tim I. Manherz
Feng Mu
Nigel K. Parkes
Jan R. Prusinski
David Richardson

Peter J. Ruttura
Gregory M. Scurto
Scott M. Tarr
Eduardo Tartuce
Eldon G. Tipping
Robert L. Varner
Steven M. Waalkes

Consulting Members

Jerry A. Holland

Jon I. Mullarky

David M. Suchorski

Concrete parking lots serve many kinds of public facilities, commercial and retail developments, businesses, and multifamily housing projects. They primarily accommodate parked vehicles but may also provide maneuvering areas and access for delivery vehicles. The design and construction of concrete slabs for parking lots and outside storage areas share many similarities with the design and construction of industrial pavements, streets, and highways, but they also have some very distinct differences. A full appreciation of the differences and the modification of design and construction procedures to take these differences into account can result in economical concrete parking lots that will provide satisfactory service for many years with little maintenance.

This guide includes information on site investigation, thickness determination, design of joints and other details, durability considerations, paving operations, and quality-assurance procedures during construction. Maintenance and repair are also discussed.

Information related to the design and construction of concrete site paving for industrial and trucking facilities is in ACI 330.2R.

Keywords: commercial; concrete pavement; curing; finishing; joints; light duty; parking lot; subgrade; thickness; traffic loads.

CONTENTS

CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

- 1.1—Introduction, p. 2
- 1.2—Scope, p. 3

CHAPTER 2—NOTATION AND DEFINITIONS, p. 4

- 2.1—Notation, p. 4
- 2.2—Definitions, p. 5

CHAPTER 3—PAVEMENT DESIGN, p. 5

- 3.1—Introduction, p. 5
- 3.2—Pavement stresses and cracking, p. 6
- 3.3—Traffic loads, p. 6
- 3.4—Subgrade support, p. 6
- 3.5—Concrete properties, p. 7
- 3.6—Thickness design, p. 7

ACI Committee Reports and Guides are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI PRC-330-21 supersedes ACI 330R-08 and was adopted and published May 2021.

Copyright © 2021, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

- 3.7—Jointing, p. 9
- 3.8—Steel reinforcement in parking lot pavements, p. 10
- 3.9—Fiber reinforcement in parking lot pavements, p. 11
- 3.10—Joint filling and sealing, p. 11
- 3.11—Pavement grades, p. 12
- 3.12—ADA/ABA-AG surface profile requirements, p. 12
- 3.13—Other design features, p. 12
- 3.14—Design examples, p. 13

CHAPTER 4—CONCRETE MATERIALS AND MIXTURE PROPORTIONING, p. 13

- 4.1—Introduction, p. 13
- 4.2—Cementitious materials, p. 13
- 4.3—Mixing water, p. 14
- 4.4—Aggregates, p. 14
- 4.5—Admixtures, p. 14
- 4.6—Fibers, p. 15
- 4.7—Concrete mixture analysis, p. 16

CHAPTER 5—CONSTRUCTION, p. 18

- 5.1—Introduction, p. 18
- 5.2—Subgrade and Subbase preparation, p. 19
- 5.3—Layout for construction, p. 20
- 5.4—Forming and the use of rigid screed guides, p. 21
- 5.5—Concrete placement, screeding, and finishing, p. 21
- 5.6—Tools and equipment for placing and finishing, p. 26
- 5.7—Installation of the different joint types, p. 26
- 5.8—Joint sealing or filling, p. 29
- 5.9—Curing, p. 29
- 5.10—Special considerations for adverse weather conditions, p. 29
- 5.11—Striping, p. 30
- 5.12—Opening to traffic, p. 31

CHAPTER 6—INSPECTION AND TESTING, p. 31

- 6.1—Introduction, p. 31
- 6.2—Site preparation and grading, p. 31
- 6.3—Subgrade and subbase, p. 31
- 6.4—Forming, p. 32
- 6.5—Reinforcing steel, p. 32
- 6.6—Concrete quality, p. 33
- 6.7—Concrete curing, p. 33
- 6.8—Jointing, p. 34
- 6.9—Surface texture, p. 34
- 6.10—Thickness testing, p. 34

CHAPTER 7—MAINTENANCE AND REPAIR, p. 34

- 7.1—Introduction, p. 34
- 7.2—Surface sealing, p. 34
- 7.3—Joint resealing and crack sealing, p. 34
- 7.4—Partial-depth repair, p. 35
- 7.5—Full-depth repair, p. 35
- 7.6—Stabilization and slab jacking, p. 35
- 7.7—Parking lot cleaning, p. 35

CHAPTER 8—REFERENCES, p. 35

- Referenced standards and reports, p. 35
- Authored references, p. 37

APPENDIX A—PROCEDURES FOR CONCRETE PAVEMENT DESIGN, p. 38

- A.1—Source of thickness tables, p. 38
- A.2—AASHTO procedure, p. 39

APPENDIX B—SUBGRADE, p. 39

- B.1—Introduction, p. 39
- B.2—Soil classification, p. 39
- B.3—Problem soils, p. 39
- B.4—Expansive soils, p. 39
- B.5—Frost action, p. 40
- B.6—Pumping, p. 40
- B.7—Support uniformity, p. 40

APPENDIX C—SUGGESTED DETAILS, p. 41

- C.1—Pavement jointing and design feature details, p. 41

APPENDIX D—PARKING LOT GEOMETRICS, p. 43

- D.1—Parking requirements, p. 43
- D.2—Entrances and exits, p. 43
- D.3—Truck maneuvering areas, p. 43
- D.4—Additional information, p. 45

APPENDIX E—DESIGN EXAMPLE: STRIP MALL, p. 45

- E.1—Geotechnical/materials engineering report, p. 45
- E.2—Loading data and traffic patterns, p. 45
- E.3—Pavement area thickness and joint spacing design, p. 45
- E.4—Tie-bars, dowels, and reinforcement, p. 47
- E.5—Joint types, location, and sealing, p. 47
- E.6—Curbs, p. 48
- E.7—Panel sliding, p. 48
- E.8—Texture, p. 48
- E.9—Slopes, p. 48
- E.10—Parking space layout (unless otherwise required by local ordinances), p. 48
- E.11—Concrete mixture, p. 48

APPENDIX F—FIBER JOINT SPACING, p. 48

CHAPTER 1—INTRODUCTION AND SCOPE

1.1—Introduction

Concrete parking lots serve many different types of facilities and are generally similar in design and construction to other types of concrete pavements. They differ, however, in that the primary role of a parking lot is typically to accommodate storage of vehicles rather than moving traffic, and the pavement loads and geometry differ accordingly. Parking lots tend to be designed for slower vehicle movement, more random traffic patterns, and fewer design load repetitions than streets, highways, airport runways, intermodal yards, and industrial or trucking facility pavements.

The design of concrete parking lots should follow the generally accepted procedures outlined in this guide. Load-bearing capacity, drainage, crack control, life-cycle cost, constructability, safety, sustainability, and maintainability are important considerations that impact good design.

Concrete parking lots may be designed to accommodate light vehicles, heavy trucks, or a broad spectrum of vehicle loads as appropriate for the application. Where a variety of loads must be accommodated, the use of traffic controls to separate and channel the heavier trucks away from areas designed for automobiles and light trucks will result in a more economical and sustainable design. Facilities intended to serve only light vehicles may have concrete parking lot panels with thicknesses influenced by constructability and environmental effects rather than by the pavement stress created by vehicle loads. Durability-related distress is often the most critical maintenance concern for lightly loaded concrete parking lot pavements, which are subject to the effects of fuels and lubricants leaked from vehicles, precipitation and drainage, deicer salts, and other environmental influences. Vehicles in parking areas usually travel at low speeds, diminishing the importance of smoothness tolerances. Because parking lots must also accommodate pedestrians, designs and geometrics should reflect pedestrian safety considerations, including crosswalks, a slip-resistant surface texture, and night-time illumination.

Concrete parking lots range in size from small, such as at corner convenience stores, to medium, such as at multi-unit housing projects, to large, such as those for shopping centers and office or commercial developments. Most parking areas include driveways, some of which must accommodate relatively heavy loads. Special consideration may be needed if access to garbage trucks, dumpsters, and/or delivery trucks is to be included. Accordingly, concrete parking lots are constructed with a wide variety of construction equipment, ranging from hand tools and vibratory screeds to large highway paving equipment or laser-guided screeds.

The stiffness of rigid concrete pavements distributes wheel loads over larger areas of the subgrade than do flexible asphalt pavements, resulting in lower subgrade stresses. Thus, thinner total pavement structures are usually possible for a given site when concrete is used. Additional benefits of concrete parking lots include the following:

- a) Concrete surfaces resist deformation from maneuvering vehicles
- b) Concrete surfaces drain well with only minimal slopes
- c) Concrete has relatively simple maintenance requirements
- d) Traffic-lane and parking-stall markings can be incorporated into the jointing pattern
- e) Concrete is minimally affected by leaking petroleum products
- f) The light-reflective surface of concrete can be efficiently illuminated with minimal energy requirements
- g) Concrete parking lots reduce the impacts of the urban heat island effect relative to those of asphalt parking lots by producing lower surface temperatures, thus providing a cooler urban environment and reducing ozone production.

The sustainable construction benefits of concrete are considerable as compared with other pavement materials. Concrete parking lots typically have service lives of 20 years or more, negating the need for more frequent rehabilitation that would use additional aggregates and other nonrenewable resources. In addition to opportunities for

the use of sustainable concrete component materials such as recycled aggregates and supplementary cementitious materials derived from industrial by-products, concrete's light-colored surface helps reduce reflected solar radiation, and its higher reflectivity can reduce illumination requirements considerably. Lower resulting energy requirements are realized throughout the facility's life cycle. Pervious concrete may be useful in reducing storm water runoff from the site (refer to [ACI 522R](#)). At the end of the service life, concrete can be recycled into aggregates and pavement subbase materials. These and other attributes of concrete can be useful in obtaining LEED Green Building certification for a project ([NRMCA 2014](#)).

1.2—Scope

This guide is based on the current knowledge and best practices for the design, construction, and maintenance of concrete parking lots placed on the ground. Some of these practices differ from those used in the design and construction of streets, highways, floors and other types of pavements and flatwork. This guide is not a standard or a specification, and it is not intended to be included by reference in construction contract documents; [ACI 330.1](#) can be used for these purposes.

Parking lots have most loads imposed on interior slabs surrounded by other pavement. Highway and street pavements carry heavy loads along and across free edges and are subjected to greater deflections and stresses. Streets and pavements are usually designed to drain toward an edge where the water can be carried away from the pavement. Parking lots are usually designed so some of the water is collected internally and is conveyed away through underground systems. In urban areas where rainfall runoff from large impervious surfaces is regulated, parking lots often serve as detention basins (not addressed in this guide). This means that the pavement should store water for a period of time without incurring any damage due to loss of support from a saturated subgrade. Parking lots often accommodate appurtenances, such as lighting standards, drainage structures, traffic islands, and landscaped planting areas. Provisions for these appurtenances should be considered in the design of the jointing system and the layout for construction.

Some design methods for concrete parking lot pavements have been based on methods developed for the design of highway pavements such as the [Portland Cement Association \(1984a,b\)](#) method and the [AASHTO \(1993\)](#) design method. These methods are primarily concerned with limiting stresses in the slab (PCA) and the reductions in serviceability caused by mixed traffic (PCA and AASHTO), including heavy trucks, while parking lots usually serve fewer vehicles either parked or traveling at slow speeds. Additionally, AASHTO (1993) is a purely empirical method where the relevant range of vehicle types, subbase and subgrade materials, and pavement repetitions are generally outside of the relevant range for parking lots. Figure 1.2 presents a typical section through a concrete pavement showing subbase and subgrade layers. For many parking lots intended for only light traffic loads, the need for an extensive design process may be less