

ACI 350-06

**Code Requirements for
Environmental Engineering
Concrete Structures
and Commentary (ACI 350-06)**

An ACI Standard

Reported by ACI Committee 350



American Concrete Institute®

CODE REQUIREMENTS FOR ENVIRONMENTAL ENGINEERING CONCRETE STRUCTURES (ACI 350-06) AND COMMENTARY

REPORTED BY ACI COMMITTEE 350

ACI Committee 350
Environmental Engineering Concrete Structures

Satish K. Sachdev
Chair

Jon B. Ardahl
Vice Chair

John W. Baker
Secretary

Walter N. Bennett
Lucian I. Bogdan
Steven R. Close
Patrick J. Creegan
Robert E. Doyle
Anthony L. Felder

Carl A. Gentry
Gautam Ghosh
Charles S. Hanskat
Keith W. Jacobson
M. Reza Kianoush

Nicholas A. Legatos
Ramon E. Lucero
Andrew R. Minogue
Lawrence G. Mrazek
Javeed A. Munshi

Jerry Parnes
Andrew R. Philip
Risto Protic
William C. Sherman
Lawrence M. Tabat

Voting Subcommittee Members

Iyad (Ed) M. Alsamsam
Paul Hedli
Lawrence E. Kaiser
Salvatore Marques

Daniel J. McCarthy
Carl H. Moon
Rolf P. Pawski
Paul J. St. John

Consulting Members

William Irwin
Dov Kaminetzky
David G. Kittridge

Dennis C. Kohl
Terry Patzias
Narayan M. Prachand

CODE REQUIREMENTS FOR ENVIRONMENTAL ENGINEERING CONCRETE STRUCTURES (ACI 350-06) AND COMMENTARY

REPORTED BY ACI COMMITTEE 350

The code portion of this document covers the structural design, materials selection, and construction of environmental engineering concrete structures. Such structures are used for conveying, storing, or treating liquid or other materials such as solid waste. They include ancillary structures for dams, spill-ways, and channels.

They are subject to uniquely different loadings, more severe exposure conditions, and more restrictive serviceability requirements than non-environmental building structures.

Loadings include normal dead and live loads and vibrating equipment or hydrodynamic forces. Exposures include concentrated chemicals, alternate wetting and drying, and freezing and thawing of saturated concrete. Serviceability requirements include liquid-tightness or gas-tightness.

Typical structures include conveyance, storage, and treatment structures.

Proper design, materials, and construction of environmental engineering concrete structures are required to produce serviceable concrete that is dense, durable, nearly impermeable, and resistant to chemicals, with limited deflections and cracking. Leakage must be controlled to minimize contamination of ground water or the environment, to minimize loss of product or infiltration, and to promote durability.

This code presents new material as well as modified portions of the ACI 318-02 Building Code that are applicable to environmental engineering concrete structures.

Because ACI 350-06 is written as a legal document, it may be adopted by reference in a general building code or in regulations governing the design and construction of environmental engineering concrete structures. Thus, it cannot present background details or suggestions for carrying out its requirements or intent. It is the function of the commentary to fill this need.

ACI 350-06 was adopted as a standard of the American Concrete Institute on July 3, 2006 to supersede ACI 350/350R-01 in accordance with the Institute's standardization procedure.

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This Commentary is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or

damage arising therefrom. Reference to this commentary shall not be made in contract documents. If items found in this Commentary are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

Copyright © 2006, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by any electronic or mechanical device, printed or written or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

The 2006 “Code Requirements for Environmental Engineering Concrete Structures and Commentary” are presented in a side-by-side column format, with code text placed in the left column and the corresponding commentary text aligned in the right column. To further distinguish the Code from the Commentary, the Code has been printed in Helvetica, the same type face in which this paragraph is set.

This paragraph is set in Times Roman, and all portions of the text exclusive to the Commentary are printed in this type face. Commentary section numbers are preceded by an “R” to further distinguish them from Code section numbers.

The commentary discusses some of the considerations of the committee in developing the ACI 350 Code, and its relationship with ACI 318. Emphasis is given to the explanation of provisions that may be unfamiliar to some users of the code. References to much of the research data referred to in preparing the code are given for those who wish to study certain requirements in greater detail.

The chapter and section numbering of the code are followed throughout the commentary.

Among the subjects covered are: permits, drawings and specifications, inspections, materials, concrete quality, mixing and placing, forming, embedded pipes, construction joints, reinforcement details, analysis and design, strength and serviceability, flexural and axial loads, shear and torsion, development of reinforcement, slab systems, walls, footings, precast concrete, prestressed concrete, shell structures, folded plate members, provisions for seismic design, and an alternate design method in Appendix I.

The quality and testing of materials used in the construction are covered by reference to the appropriate standard specifications. Welding of reinforcement is covered by reference to the appropriate AWS standard. Criteria for liquid-tightness testing may be found in 350.1.

Keywords: Chemical attack; coatings; concrete durability; concrete finishing (fresh concrete); concrete slabs, crack width, and spacing; cracking (fracturing); environmental engineering; inspection; joints (junctions); joint sealers; liquid; patching; permeability; pipe columns; pipes (tubes); prestressed concrete; prestressing steels; protective coatings; reservoirs; roofs; serviceability; sewerage; solid waste facilities; tanks (containers); temperature; torque; torsion; vibration; volume change; walls; wastewater treatment; water; water-cementitious material ratio; water supply; water treatment.

INTRODUCTION

The code and commentary includes excerpts from ACI 318-02 that are pertinent to ACI 350. The commentary discusses some of the considerations of Committee ACI 350 in developing “Code Requirements for Environmental Engineering Concrete Structures (ACI 350-06),” hereinafter called the code. Emphasis is given to the explanation of provisions that may be unfamiliar to users of the standard. Comments on specific provisions are made under the corresponding chapter and section numbers of the code and commentary.

This commentary is not intended to provide a complete historical background concerning the development of the code, nor is it intended to provide a detailed summary of the studies and research data reviewed by the committee in formulating the provisions of the code. However, references to some of the research data are provided for those who wish to study the background material in depth.

As the name implies, “Code Requirements for Environmental Engineering Concrete Structures” may be used as part of a legally adopted code and, as such, must differ in form and substance from documents that provide detailed specifications, recommended practice, complete design procedures, or design aids.

The code is intended to cover environmental engineering concrete structures, but is not intended to supersede ASTM standards for precast structures.

Requirements more stringent than the code provisions may be desirable for unusual structures. This code and this commentary cannot replace sound engineering knowledge, experience, and judgment.

A code for design and construction states the minimum requirements necessary to provide for public health and safety. ACI 350 is based on this principle. For any structure, the owner or the structural designer may require the quality of materials and construction to be higher than the minimum requirements necessary to provide serviceability and to protect the public as stated in the code. Lower standards, however, are not permitted.

ACI 350 has no legal status unless it is adopted by government bodies having the power to regulate building design and construction. Where the code has not been adopted, it may serve as a reference to good practice.

The code provides a means of establishing minimum standards for acceptance of design and construction by a legally appointed building official or his designated representatives. The code and commentary are not intended for use in settling disputes between the owner, engineer, architect, contractor, or their agents, subcontractors, material suppliers, or testing agencies. Therefore, the code cannot define the contract responsibility of each of the parties in usual construction. General references requiring compliance with ACI 350 in the job specifications should be avoided, since the contractor is rarely in a position to accept responsibility for design

details or construction requirements that depend on a detailed knowledge of the design. Generally, the drawings, specifications, and contract documents should contain all of the necessary requirements to ensure compliance with the code. In part, this can be accomplished by reference to specific code sections in the job specifications. Other ACI publications, such as ACI 301, "Specifications for Structural Concrete," are written specifically for use as contract documents for construction.

Committee 350 recognizes the desirability of standards of performance for individual parties involved in the contract documents. Available for this purpose are the certification programs of the American Concrete Institute, the plant certification programs of the Precast/Prestressed Concrete Institute, the National Ready Mixed Concrete Association, and the qualification standards of the American Society of Concrete Constructors. Also available are "Standard Specification for Agencies Engaged in Construction Inspection and/or Testing" (ASTM E 329) and "Standard Practice for Laboratories Testing Concrete and Concrete Aggregates for Use in Construction and Criteria for Laboratory Evaluation" (ASTM C 1077).

Design aids (general concrete design aids are listed in ACI 318-02):

"Rectangular Concrete Tanks," Portland Cement Association, Skokie, IL, 1994, 176 pp. (Presents data for design of rectangular tanks.)

"Circular Concrete Tanks Without Prestressing," Portland Cement Association, Skokie, IL, 1993, 54 pp. (Presents design data for circular concrete tanks built in or on ground. Walls may be free or restrained at the top. Wall bases may be fixed, hinged, or have intermediate degrees of restraint. Various layouts for circular roofs are presented.)

"Concrete Manual," U.S. Department of Interior, Bureau of Reclamation, 8th edition, 1981, 627 pp. (Presents technical information for the control of concrete construction, including linings for tunnels, impoundments, and canals.)

GENERAL COMMENTARY

Because of stringent service requirements, environmental engineering concrete structures should be designed and detailed with care. The quality of concrete is important, and close quality control must be performed during construction to obtain impervious concrete.

Environmental engineering concrete structures for the containment, treatment, or transmission of liquid such as water and wastewater as well as solid waste disposal facilities, should be designed and constructed to be essentially liquid-tight, with minimal leakage under normal service conditions.

The liquid-tightness of a structure will be reasonably assured if:

- a) The concrete mixture is well proportioned, well consolidated without segregation, and properly cured.
- b) Crack widths and depths are minimized.
- c) Joints are properly spaced, sized, designed, water-stopped, and constructed.
- d) Adequate reinforcing steel is provided, properly detailed, fabricated, and placed.
- e) Impervious protective coatings or barriers are used where required.

Usually it is more economical and dependable to resist liquid permeation through the use of quality concrete, proper design of joint details, and adequate reinforcement, rather than by means of an impervious protective barrier or coating. Liquid-tightness can also be obtained by appropriate use of shrinkage-compensating concrete. However, to achieve success, the engineer must recognize and account for the limitations, characteristics, and properties of shrinkage-compensating concrete as described in ACI 223 and ACI 224.2R.

Minimum permeability of the concrete will be obtained by using water-cementitious materials ratios as low as possible, consistent with satisfactory workability and consolidation. Impermeability increases with the age of the concrete and is improved by extended periods of moist curing. Surface treatment is important and use of smooth forms or troweling improves impermeability. Air entrainment reduces segregation and bleeding, increases workability, and provides resistance to the effect of freeze-thaw cycles. Because of this, use of an air-entraining admixture results in better consolidated concrete. Other admixtures, such as water-reducing agents and pozzolans, are useful when they lead to increased workability and consolidation, and lower water-cementitious ratios. Pozzolans also reduce permeability.

Joint design should also account for movement resulting from thermal dimensional changes and differential settlements. Joints permitting movement along predetermined control planes, and which form a barrier to the passage of fluids, shall include waterstops in complete, closed circuits. Proper rate of concrete placement operations, adequate consolidation, and proper curing are also essential to control of cracking in environmental engineering concrete structures. Additional information on cracking is contained in ACI 224R and ACI 224.2R.

The design of the whole environmental engineering concrete structure as well as all individual members should be in accordance with ACI 350-06, which has been adapted from ACI 318-02. When all relevant loading conditions are considered, the design should provide adequate safety and serviceability, with a life expectancy of 50 to 60 years for the structural concrete. Some components of the structure, such as jointing materials, have a shorter life expectancy and will require maintenance or replacement.

The size of elements and amount of reinforcement should be selected on the basis of the serviceability crack-width limits and stress limits to promote long service life.

CONTENTS

PART 1—GENERAL

CHAPTER 1—GENERAL REQUIREMENTS 9

- 1.1—Scope
- 1.3—Inspection
- 1.2—Drawings and specifications
- 1.4—Approval of special systems of design or construction

CHAPTER 2—DEFINITIONS 21

PART 2—STANDARDS FOR TESTS AND MATERIALS

CHAPTER 3—MATERIALS 31

- 3.0—Notation
- 3.5—Steel reinforcement
- 3.1—Tests of materials
- 3.6—Admixtures
- 3.2—Cements
- 3.7—Storage of materials
- 3.3—Aggregates
- 3.8—Reference standards
- 3.4—Water

PART 3—CONSTRUCTION REQUIREMENTS

CHAPTER 4—DURABILITY REQUIREMENTS 47

- 4.0—Notation
- 4.4—Corrosion protection of metals
- 4.1—Water-cementitious materials ratio and
cementitious material content
- 4.5—Chemical effects
- 4.2—Freezing and thawing exposures
- 4.6—Protection against erosion
- 4.3—Sulfate exposures
- 4.7—Coatings and liners
- 4.8—Joints

CHAPTER 5—CONCRETE QUALITY, MIXING, AND PLACING 63

- 5.0—Notation
- 5.6—Preparation of equipment and place of deposit
- 5.1—General
- 5.7—Mixing
- 5.2—Selection of concrete proportions
- 5.8—Conveying
- 5.3—Proportioning on the basis of field experience,
trial mixtures, or both
- 5.9—Depositing
- 5.4—Average strength reduction
- 5.10—Curing
- 5.5—Evaluation and acceptance of concrete
- 5.11—Cold weather requirements
- 5.12—Hot weather requirements

CHAPTER 6—FORMWORK, EMBEDDED PIPES, AND CONSTRUCTION AND MOVEMENT JOINTS..... 79

- 6.1—Design of formwork
- 6.4—Construction joints
- 6.2—Removal of forms, shores, and reshoring
- 6.5—Movement joints
- 6.3—Conduits and pipes embedded in concrete

CHAPTER 7—DETAILS OF REINFORCEMENT 85

- 7.0—Notation
- 7.7—Concrete protection for reinforcement
- 7.1—Standard hooks
- 7.8—Special reinforcement details for columns
- 7.2—Minimum bend diameters
- 7.9—Connections
- 7.3—Bending
- 7.10—Lateral reinforcement for compression members
- 7.4—Surface conditions of reinforcement
- 7.11—Lateral reinforcement for flexural members
- 7.5—Placing reinforcement
- 7.12—Shrinkage and temperature reinforcement
- 7.6—Spacing limits for reinforcement
- 7.13—Requirements for structural integrity

PART 4—GENERAL REQUIREMENTS

CHAPTER 8—ANALYSIS AND DESIGN—GENERAL CONSIDERATIONS 101

- | | |
|---|------------------------------|
| 8.0—Notation | 8.6—Stiffness |
| 8.1—Design methods | 8.7—Span length |
| 8.2—Loading | 8.8—Columns |
| 8.3—Methods of analysis | 8.9—Arrangement of live load |
| 8.4—Redistribution of negative moments in continuous flexural members | 8.10—T-beam construction |
| 8.5—Modulus of elasticity | 8.11—Joist construction |
| | 8.12—Separate floor finish |

CHAPTER 9—STRENGTH AND SERVICEABILITY REQUIREMENTS..... 111

- | | |
|-----------------------|---------------------------------------|
| 9.0—Notation | 9.3—Design strength |
| 9.1—General | 9.4—Design strength for reinforcement |
| 9.2—Required strength | 9.5—Control of deflections |

CHAPTER 10—FLEXURE AND AXIAL LOADS..... 127

- | | |
|--|---|
| 10.0—Notation | 10.9—Limits for reinforcement of compression members |
| 10.1—Scope | 10.10—Slenderness effects in compression members |
| 10.2—Design assumptions | 10.11—Magnified moments—General |
| 10.3—General principles and requirements | 10.12—Magnified moments—Nonsway frames |
| 10.4—Distance between lateral supports of flexural members | 10.13—Magnified moments—Sway frames |
| 10.5—Minimum reinforcement of flexural members | 10.14—Axially loaded members supporting slab system |
| 10.6—Distribution of flexural reinforcement | 10.15—Transmission of column loads through floor system |
| 10.7—Deep beams | 10.16—Composite compression members |
| 10.8—Design dimensions for compression members | 10.17—Bearing strength |

CHAPTER 11—SHEAR AND TORSION 159

- | | |
|---|--|
| 11.0—Notation | 11.6—Design for torsion |
| 11.1—Shear strength | 11.7—Shear-friction |
| 11.2—Lightweight concrete | 11.8—Deep beams |
| 11.3—Shear strength provided by concrete for nonprestressed members | 11.9—Special provisions for brackets and corbels |
| 11.4—Shear strength provided by concrete for prestressed members | 11.10—Special provisions for walls |
| 11.5—Shear strength provided by shear reinforcement | 11.11—Transfer of moments to columns |
| | 11.12—Special provisions for slabs and footings |

CHAPTER 12—DEVELOPMENT AND SPLICES OF REINFORCEMENT 205

- | | |
|--|---|
| 12.0—Notation | 12.9—Development of prestressing strand |
| 12.1—Development of reinforcement—General | 12.10—Development of flexural reinforcement—General |
| 12.2—Development of deformed bars and deformed wire in tension | 12.11—Development of positive moment reinforcement |
| 12.3—Development of deformed bars and deformed wire in compression | 12.12—Development of negative moment reinforcement |
| 12.4—Development of bundled bars | 12.13—Development of web reinforcement |
| 12.5—Development of standard hooks in tension | 12.14—Splices of reinforcement—General |
| 12.6—Mechanical anchorage | 12.15—Splices of deformed bars and deformed wire in tension |
| 12.7—Development of welded deformed wire fabric in tension | 12.16—Splices of deformed bars in compression |
| 12.8—Development of welded plain wire fabric in tension | 12.17—Special splice requirements for columns |
| | 12.18—Splices of welded deformed wire fabric in tension |
| | 12.19—Splices of welded plain wire fabric in tension |

PART 5—STRUCTURAL SYSTEMS OR ELEMENTS**CHAPTER 13—TWO-WAY SLAB SYSTEMS 233**

- | | |
|-------------------------|-------------------------------|
| 13.0—Notation | 13.4—Openings in slab systems |
| 13.1—Scope | 13.5—Design procedures |
| 13.2—Definitions | 13.6—Direct design method |
| 13.3—Slab reinforcement | 13.7—Equivalent frame method |

CHAPTER 14—WALLS 253

- | | |
|--|--|
| 14.0—Notation | 14.5—Empirical design method |
| 14.1—Scope | 14.6—Minimum wall thickness |
| 14.2—General | 14.7—Walls as grade beams |
| 14.3—Minimum reinforcement | 14.8—Alternative design of slender walls |
| 14.4—Walls designed as compression members | |

CHAPTER 15—FOOTINGS 259

- | | |
|---|---|
| 15.0—Notation | 15.6—Development of reinforcement in footings |
| 15.1—Scope | 15.7—Minimum footing depth |
| 15.2—Loads and reactions | 15.8—Transfer of force at base of column, wall,
or reinforced pedestal |
| 15.3—Footings supporting circular or regular polygon
shaped columns or pedestals | 15.9—Sloped or stepped footings |
| 15.4—Moment in footings | 15.10—Combined footings and mats |
| 15.5—Shear in footings | |

CHAPTER 16—PRECAST CONCRETE 267

- | | |
|---|---|
| 16.0—Notation | 16.6—Connection and bearing design |
| 16.1—Scope | 16.7—Items embedded after concrete placement |
| 16.2—General | 16.8—Marking and identification |
| 16.3—Distribution of forces among members | 16.9—Handling |
| 16.4—Member design | 16.10—Strength evaluation of precast construction |
| 16.5—Structural integrity | |

CHAPTER 17—COMPOSITE CONCRETE FLEXURAL MEMBERS 275

- | | |
|---------------|--------------------------------|
| 17.0—Notation | 17.4—Vertical shear strength |
| 17.1—Scope | 17.5—Horizontal shear strength |
| 17.2—General | 17.6—Ties for horizontal shear |
| 17.3—Shoring | |

CHAPTER 18—PRESTRESSED CONCRETE 279

- | | |
|---|--|
| 18.0—Notation | 18.12—Slab systems |
| 18.1—Scope | 18.13—Post-tensioned tendon anchorage zones |
| 18.2—General | 18.14—Design of anchorage zones for monostrand or
single 5/8 in. diameter bar tendons |
| 18.3—Design assumptions | 18.15—Design of anchorage zone for multistrand tendons |
| 18.4—Serviceability requirements—Flexural members | 18.16—Corrosion protection for unbonded single-strand
prestressing tendons |
| 18.5—Permissible stresses in prestressing steel | 18.17—Post-tensioning ducts |
| 18.6—Loss of prestress | 18.18—Grout for bonded tendons |
| 18.7—Flexural strength | 18.19—Protection for prestressing steel |
| 18.8—Limits for reinforcement of flexural members | 18.20—Application and measurement of prestressing force |
| 18.9—Minimum bonded reinforcement | 18.21—Post-tensioning anchorages and couplers |
| 18.10—Statically indeterminate structures | 18.22—External post-tensioning |
| 18.11—Compression members—Combined flexure and
axial loads | |

CHAPTER 19—SHELLS AND FOLDED PLATE MEMBERS..... 311

- | | |
|----------------------------|-----------------------------------|
| 19.0—Notation | 19.3—Design strength of materials |
| 19.1—Scope and definitions | 19.4—Shell reinforcement |
| 19.2—Analysis and design | 19.5—Construction |

PART 6—SPECIAL CONSIDERATIONS**CHAPTER 20—STRENGTH EVALUATION OF EXISTING STRUCTURES 319**

- | | |
|---|--------------------------------------|
| 20.0—Notation | 20.4—Loading criteria |
| 20.1—Strength evaluation—General | 20.5—Acceptance criteria |
| 20.2—Determination of required dimensions and material properties | 20.6—Provision for lower load rating |
| 20.3—Load test procedure | 20.7—Safety |

CHAPTER 21—SPECIAL PROVISIONS FOR SEISMIC DESIGN..... 325

- | | |
|---|---|
| 21.0—Notation | 21.8—Special structural walls constructed using precast concrete |
| 21.1—Definitions | 21.9—Structural diaphragms and trusses |
| 21.2—General requirements | 21.10—Foundations |
| 21.3—Flexural members of special moment frames | 21.11—Frame members not proportioned to resist forces induced by earthquake motions |
| 21.4—Special moment frame members subjected to bending and axial load | 21.12—Requirements for intermediate moment frames |
| 21.5—Joints of special moment frames | 21.13—Intermediate precast structural walls |
| 21.6—Special moment frames constructed using precast concrete | |
| 21.7—Special reinforced concrete structural walls and coupling beams | |

PART 7—STRUCTURAL PLAIN CONCRETE**CHAPTER 22—STRUCTURAL PLAIN CONCRETE 367****COMMENTARY REFERENCES 369****APPENDIXES****APPENDIX A—NOT USED..... 387****APPENDIX B—ALTERNATE PROVISIONS FOR REINFORCED AND PRESTRESSED CONCRETE FLEXURAL AND COMPRESSION MEMBERS 389**

- | | |
|--------------|-----------|
| B.0—Notation | B.1—Scope |
|--------------|-----------|

APPENDIX C—ALTERNATE LOAD FACTORS, STRENGTH REDUCTION FACTORS, AND DISTRIBUTION OF FLEXURAL REINFORCEMENT 393

- | |
|-------------|
| C.1—General |
|-------------|

APPENDIX D—ANCHORING TO CONCRETE..... 401

- | | |
|--|--|
| D.0—Notation | D.6—Design requirements for shear loading |
| D.1—Definitions | D.7—Interaction of tensile and shear forces |
| D.2—Scope | D.8—Required edge distances, spacings, and thicknesses to preclude splitting failure |
| D.3—General requirements | D.9—Installation of anchors |
| D.4—General requirements for strength of anchors | |
| D.5—Design requirements for tensile loading | |

APPENDIX E—NOTATION..... 427

APPENDIX F—METAL REINFORCEMENT INFORMATION..... 441

**APPENDIX G—CIRCULAR WIRE AND STRAND WRAPPED
PRESTRESSED CONCRETE ENVIRONMENTAL
STRUCTURES..... 443**

G.0—Notation
G.1—Scope
G.2—Design

G.3—Materials
G.4—Construction procedures

APPENDIX H—SLABS-ON-SOIL 459

H.1—Scope
H.2—Subgrade
H.3—Slab thickness
H.4—Reinforcement

H.5—Joints
H.6—Hydrostatic uplift
H.7—Curing

APPENDIX I—ALTERNATE DESIGN METHOD..... 463

I.0—Notation
I.1—Scope
I.2—General
I.3—Permissible service load stresses

I.4—Development and splices of reinforcement
I.5—Flexure
I.6—Compression members with or without flexure
I.7—Shear and torsion

INDEX 475

SUMMARY OF CHANGES FOR 350-06 CODE 481

PART 1 — GENERAL

CHAPTER 1 — GENERAL REQUIREMENTS

CODE

1.1 — Scope

COMMENTARY

R1.1 — Scope

The American Concrete Institute “**Code Requirements for Environmental Engineering Concrete Structures (ACI 350-06)**,” hereinafter referred to as the code, provide minimum requirements for environmental engineering concrete structural design and construction practices.

The 2006 edition of the code revised the previous code, “**Code Requirements of Environmental Engineering Concrete Structures (ACI 350-01)**.” This code includes in one document the rules for all reinforced concrete used for environmental engineering structural purposes. This covers the spectrum of structural applications of concrete containing nonprestressed reinforcement, prestressing steel, or composite steel shapes, pipe, or tubing.

Prestressed concrete is included under the definition of reinforced concrete. Provisions of ACI 350-06 apply to prestressed concrete except in cases in which the provisions of the code are stated to apply specifically to nonprestressed concrete.

Chapter 21 of the code contains special provisions for design and detailing of earthquake-resistant structures. See 1.1.8.

Appendix I of the 2006 code, formerly Appendix A of the 2001 code, contains provisions for an alternate method of design for nonprestressed reinforced concrete members using service loads (without load factors) and permissible service load stresses. The strength design method of this code is intended to give design results similar to the Alternate Design Method.

Appendix A of the ACI 318-02 code has not yet been adopted for environmental engineering concrete structures. Applicability of strut-and-tie models to environmental structures may be addressed in future revisions to ACI 350.

Appendix B of the 2006 code contains provisions for reinforcement limits based on $0.75\rho_b$, determination of the strength reduction factor ϕ , and moment redistribution that have been in the 318 codes for many years, including the 1999 318 code. The provisions are applicable to reinforced and prestressed concrete members. Designs made using the provisions of Appendix B are used in their entirety.

Appendix C of the 2006 code allows the use of load, environmental durability, strength reduction factors, and flexural reinforcement distribution provisions similar to those in Chapters 9 and 10 of ACI 350-01. Designs made using the provisions of Appendix C are equally acceptable

CODE

1.1.1 — Except for primary containment of hazardous materials, this code provides minimum requirements for the design and construction of reinforced concrete structural elements of any environmental engineering concrete structure erected under the requirements of the legally adopted building code where this code has been adopted to be a part of such code. In areas without a legally adopted building code, this code defines minimum acceptable standards of design and construction practice.

For structural concrete, the specified concrete strength shall not be less than 4000 psi. No maximum specified compressive strength shall apply unless restricted by a specific code provision.

1.1.1.1 — Environmental engineering concrete structures are defined as concrete structures intended for conveying, storing, or treating water, wastewater, or other liquids and non-hazardous materials such as solid waste, and for secondary containment of hazardous liquids or solid waste. Ancillary structures for which liquid-tightness, gas-tightness, or enhanced durability are essential design considerations shall also conform to requirements of environmental engineering concrete structures. Precast concrete environmental structures designed and constructed in accordance with ASTM or AWWA standards, with the exception of circular tanks, are not covered in this code.

1.1.2 — This code supplements the general building code and shall govern in all matters pertaining to design and construction of reinforced concrete structural elements of any environmental engineering concrete structure, except wherever this code is in conflict with requirements in legally-adopted applicable codes addressing environmental engineering concrete structures.

1.1.3 — This code shall apply in all matters pertaining to design, construction, and material properties wherever this code is in conflict with requirements contained in other standards referenced in this code.

1.1.4 — The provisions of this code shall govern for tanks, reservoirs, and other reinforced concrete elements of any environmental engineering concrete structure. Special structures such as arches, bins and silos, blast-resistant structures, and chimneys are not covered in this code.

COMMENTARY

as those based on the body of the code, provided the provisions of Appendix C are used in their entirety.

Appendix D contains provisions for anchoring to concrete.

R1.1.1 — A hazardous material is defined as having one or more of the following characteristics: ignitable (NFPA 49), corrosive, reactive, or toxic. The Environmental Protection Agency (EPA)-listed wastes are organized into three categories under RCRA: source specific wastes, generic wastes, and commercial chemical products. Source specific wastes include sludges and wastewaters from treatment and production processes in specific industries such as petroleum refining and wood preserving. The list of generic wastes includes wastes from common manufacturing and industrial processes such as solvents used in degreasing operations. The third list contains specific chemical products such as benzene, creosote, mercury, and various pesticides.

Below-grade structures, such as pump stations and pipe galleries, which are part of treatment facilities and which may be exposed to external groundwater pressures, generally are designed as environmental concrete structures. Above-grade building structures that are not directly exposed to liquids, solid wastes, corrosive chemicals, corrosive gases, or high humidity associated with treatment facilities generally may be designed in accordance with the general building code or applicable industry standards. Nevertheless, consideration of corrosive effects on such structures may still be advisable.

R1.1.2 — The American Concrete Institute recommends that the code be adopted in its entirety; however, it is recognized that when the code is made a part of a legally adopted general building code, that general building code may modify some provisions of this code.

R1.1.4 — Environmental engineering projects can contain several types of structures. For example, a treatment plant can contain environmental engineering concrete structures such as tanks and reservoirs, as well as building structures. The ACI 350 code would apply to the environmental structures, while the ACI 318 code or the following ACI publications could apply to the other structures.

“Design and Construction of Reinforced Concrete Chimneys” reported by ACI Committee 307.^{1.1} (Gives