

IN-LB

Inch-Pound Units

SI

International System of Units

Report on Deflection of Nonprestressed Concrete Structures

Reported by ACI Committee 435

ACI 435R-20



American Concrete Institute
Always advancing



Report on Deflection of Nonprestressed Concrete Structures

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised the ACI Collection of Concrete Codes, Specifications, and Practices.

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Report on Deflection of Nonprestressed Concrete Structures

Reported by ACI Committee 435

Eric S. Musselman, Chair

Dylan Freytag, Secretary

Peter H. Bischoff
Allan P. Bommer
Flora A. Calabrese
Eamonn F. Connolly
Norbert J. Delatte

Mamdouh M. El-Badry
Amin Ghali
Mayrai Gindy
Shawn P. Gross
Young Hak Lee

Adam S. Lubell
Faris A. Malhas
Michael C. Mota
Hani H. Nassif
Edward G. Nawy

Debrethann R. Orsak
Maria A. Polak
Mahmoud M. Reda Taha
Andrew Scanlon
Richard H. Scott

Consulting Members

Alex Aswad
Finley A. Charney

Satyendra Ghosh
Peter Lenkei

Bernard L. Meyers
Vilas S. Mujumdar

Himat T. Solanki
Susanto Teng

This report presents a consolidated treatment of initial and time-dependent deflection of nonprestressed reinforced concrete members such as simple and continuous beams and one-way and two-way slab systems. It presents the current state of practice of deflection prediction as well as analytical methods for computer use in deflection estimation. Topics include material properties, deflection of reinforced concrete one-way flexural members, deflection of two-way slab systems, and reducing deflection of concrete members.

Keywords: camber; cracking; creep; curvature; deflection; modulus of rupture; moments of inertia; serviceability; shrinkage; time-dependent deflection.

CONTENTS

CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

- 1.1—Introduction, p. 2
- 1.2—Scope, p. 2

CHAPTER 2—NOTATION AND DEFINITIONS, p. 3

- 2.1—Notation, p. 3
- 2.2—Definitions, p. 3

CHAPTER 3—MATERIAL PROPERTIES, p. 3

- 3.1—Objective, p. 3
- 3.2—Material properties affecting deflection, p. 4
- 3.3—Concrete material properties, p. 4
- 3.4—Reinforcement material properties, p. 9

CHAPTER 4—DEFLECTION OF REINFORCED CONCRETE ONE-WAY FLEXURAL MEMBERS, p. 9

- 4.1—General, p. 9
- 4.2—Control of deflection, p. 10
- 4.3—Short-term deflection calculation, p. 11
- 4.4—Long-term deflection calculation, p. 18
- 4.5—Temperature-induced deflections, p. 21

CHAPTER 5—DEFLECTION OF A TWO-WAY SLAB SYSTEM, p. 22

- 5.1—Introduction, p. 22
- 5.2—Deflection calculation methods for two-way slab systems, p. 23
- 5.3—Minimum thickness requirements, p. 26
- 5.4—Loads for deflection calculation, p. 28
- 5.5—Variability of deflections, p. 31
- 5.6—Allowable deflections, p. 32

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI 435R-20 supersedes ACI 435R-95(03) and became effective November 2020.
Copyright © 2020, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 6—REDUCING DEFLECTION OF CONCRETE MEMBERS, p. 32

- 6.1—Introduction, p. 32
- 6.2—Design techniques, p. 32
- 6.3—Construction techniques, p. 34
- 6.4—Materials selection, p. 35
- 6.5—Summary, p. 36

CHAPTER 7—REFERENCES, p. 36

- Authored documents, p. 36

APPENDIX A—DEFLECTION DESIGN EXAMPLES, p. 39

- Example A.1—Deflection of a simply supported slab, p. 39
- Example A.2—Age-adjusted deflection of simply supported slab, p. 43
- Example A.3—Short- and long-term deflection of a four-span continuous beam, p. 44
- Example A.4—Temperature-induced deflections, p. 48

APPENDIX B—TWO-WAY SLAB DEFLECTION EXAMPLES, p. 48

- Example B.1—Deflection design example for long-term deflection of a two-way slab, p. 48
- Example B.2—Deflection calculation for a flat plate using the crossing beam method, p. 52
- Example B.3—Minimum thickness calculation, p. 54

CHAPTER 1—INTRODUCTION AND SCOPE

1.1—Introduction

Design for serviceability is central to the work of structural engineers and code-writing bodies. It is also essential to users of the designed structures. Increased use of high-strength concrete and higher-strength reinforcing bars, coupled with more detailed computer-aided designs, has resulted in lighter and more material-efficient and, thus, more flexible structural members and systems. This in turn has necessitated better prediction and control of short-term and long-term behavior of concrete structures at service loads.

This report presents a consolidated treatment of initial and time-dependent deflection of nonprestressed reinforced concrete members such as simple and continuous beams and one- and two-way slab systems. It presents current engineering practice in design for control of deformation and deflection of concrete members and includes methods presented in **ACI 318** plus selected other approaches suitable for computer-based use in deflection computation. Design examples are given at the end of one- and two-way framing chapters showing how to evaluate deflection and, thus, control it through adequate design for serviceability. The content of the report as well as the step-by-step examples are intended to familiarize practitioners with the current methods for estimating deflections in buildings as well as analytical methods suitable for computer-based application. The examples apply **ACI 318** requirements and a recommended alternative approach with a lower cracking moment (to account for shrinkage restraint). Methods for predicting initial and time-dependent deflections

of prestressed concrete are not addressed in this document, although prestressing can be an effective tool for controlling both short- and long-term deflections.

1.2—Scope

The principal causes of deflections taken into account in this report are those due to elastic deformation, flexural cracking, creep, shrinkage, and temperature effects. This document is composed of two introductory chapters and four main chapters that provide information on calculating and controlling deflections of members constructed using reinforced concrete. The organization of the report is:

- a) **Chapter 1—Introduction and Scope** provides background information on the document.
- b) **Chapter 2—Notation and Definitions** provides a listing of the notation used throughout the document.
- c) **Chapter 3—Material Properties** discusses material properties that affect deflections.
- d) **Chapter 4—Deflection of Reinforced Concrete One-Way Flexural Members** discusses behavior of uncracked and cracked members, and time-dependent effects. It also includes the relevant code procedures and expressions for deflection computation in reinforced concrete beams. Numerical examples are included to illustrate the standard calculation methods for simply supported and continuous concrete beams.
- e) **Chapter 5—Deflection of Two-Way Slab Systems** covers the deflection behavior of reinforced two-way-action slabs and plates. This chapter gives an overview of classical and other methods of deflection estimation, such as the crossing beam analogy and the finite element method for immediate deflection computation. It also discusses approaches for determining the minimum thickness requirements for two-way slabs and plates and gives a detailed computational example for evaluating the long-term deflection of a two-way reinforced concrete slab. The chapter emphasizes the uncertainties inherent in estimating deflections of two-way slab systems.
- f) **Chapter 6—Reducing Deflection of Concrete Members** gives practical and remedial guidelines for improving and controlling the deflection of reinforced concrete members, hence enhancing their overall long-term serviceability.

It should be emphasized that the magnitude of actual deflection in concrete structural members, particularly in buildings, which are the emphasis and the intent of this report, can only be estimated with limited accuracy. This is because of the large variability in the properties of the constituent materials of these members, the quality control exercised in their construction, and the construction methods used. Therefore, for practical considerations, the computed deflection values in the illustrative examples at the end of each chapter should be interpreted with this in mind.

In summary, this single document gives design engineers the key tools for estimating, and thereby controlling through design, the expected deflection in nonprestressed reinforced concrete building structures. The material presented and the design examples will help to enhance serviceability when

used judiciously by the engineer. Designers, constructors, and codifying bodies can draw on the material presented in this document to achieve serviceable deflection of constructed facilities.

CHAPTER 2—NOTATION AND DEFINITIONS

2.1—Notation

A_s	= area of nonprestressed tension steel, in. ² (mm ²)
A_s'	= area of nonprestressed steel in compression zone, in. ² (mm ²)
b	= width of the section, in. (mm)
b_w	= web width, in. (mm)
C_t	= creep coefficient of concrete at time t , days
C_u	= ultimate creep coefficient of concrete
c	= depth of centroidal axis, in. (mm)
d	= distance from the extreme compression fiber to centroid of tension reinforcement, in. (mm)
d'	= distance from the extreme compression fiber to centroid of compression reinforcement, in. (mm)
d_b	= bar diameter, in. (mm)
E	= modulus of elasticity, psi (MPa)
E_c	= modulus of elasticity of concrete, psi (MPa)
f_c	= stress in concrete, psi (MPa)
f_c'	= specified compressive strength of concrete, psi (MPa)
f_{cr}	= stress to cause cracking in concrete, psi (MPa)
f_r	= modulus of rupture of concrete, psi (MPa)
f_{res}	= stress from restraint to shrinkage, psi (MPa)
f_s	= stress in nonprestressed steel, psi (MPa)
f_y	= specified yield strength of nonprestressed reinforcing steel, psi (MPa)
h	= overall thickness of a member, in. (mm)
h_f	= flange thickness, in. (mm)
I	= moment of inertia, in. ⁴ (mm ⁴)
I_{cr}	= moment of inertia of the cracked section transformed to concrete, in. ⁴ (mm ⁴)
I_e	= effective moment of inertia for computation of deflection, in. ⁴ (mm ⁴)
I_g	= moment of inertia for gross concrete section about centroidal axis, neglecting reinforcement, in. ⁴ (mm ⁴)
k	= depth of compression zone divided by d
ℓ	= span length, in. (mm)
ℓ_n	= distance from the inside of the support to the inside of support, clear span, in. (mm)
M	= bending moment, lb-in. (N-mm)
M_1	= moment at End 1 of a continuous member, lb-in. (N-mm)
M_2	= moment at End 2 of a continuous member, lb-in. (N-mm)
M_a	= maximum service load moment (unfactored) at stage deflection is computed, lb-in. (N-mm)
M_{cr}	= cracking moment, lb-in. (N-mm)
M_D	= moment due to dead load, lb-in. (N-mm)
M_L	= moment due to live load, lb-in. (N-mm)
M_m	= midspan moment, lb-in. (N-mm)
N	= axial member load, lb (N)
n	= modular ratio E_s/E_c
T	= temperature, °F (°C)

t	= time, s
w	= uniformly distributed load (load per unit length), lb/in. (N/mm)
w_c	= unit weight of normalweight concrete or equilibrium density of lightweight concrete, lb/ft ³ (kg/m ³)
y_t	= distance from centroidal axis of gross section, neglecting reinforcement, to extreme fiber in tension, in. (mm)
Δ	= elastic deflection of a beam or slab, in. (mm)
Δ_{cr}	= additional deflection due to creep, in. (mm)
Δ_{inc}	= incremental deflection that occurs after attachment on nonstructural elements (includes long-term deflection Δ_{LT} from sustained loads and immediate deflection from the remaining part of live load that is not sustained, in. (mm))
Δ_L	= initial (immediate) deflection due to live load, in. (mm)
Δ_{LT}	= deflection from long-term effects, in. (mm)
Δ_{sh}	= additional deflection due to shrinkage, in. (mm)
Δ_{sus}	= initial (immediate) deflection due to sustained load, in. (mm)
ϵ_{cf}	= strain due to stress in the concrete
ϵ_o	= free strain, such as unrestrained shrinkage
ϵ_{sf}	= strain due to stress in nonprestressed steel
ϵ_{sh}	= shrinkage strain of concrete
$(\epsilon_{sh})_t$	= shrinkage strain of concrete at time t , days
$(\epsilon_{sh})_u$	= ultimate shrinkage strain of concrete
ϵ_t	= total strain
ζ	= distribution coefficient
κ	= cross section curvature, in. ⁻¹ (mm ⁻¹)
κ_{sh}	= shrinkage curvature, in. ⁻¹ (mm ⁻¹)
λ_c	= creep multiplier for long-term deflection
λ_{sh}	= shrinkage warping multiplier for long-term deflection
λ_t	= total multiplier for long-term deflection
λ_{Δ}	= time-dependent multiplier for long-term deflection
ν	= Poisson's ratio
ρ	= nonprestressed tension reinforcement ratio (A_s/bd)
ρ'	= reinforcement ratio for nonprestressed compression steel (A_s'/bd)
ξ	= time-dependent multiplier for deflection

2.2—Definitions

Please refer to the latest version of ACI Concrete Terminology for a comprehensive list of definitions.

CHAPTER 3—MATERIAL PROPERTIES

3.1—Objective

Deflections in reinforced concrete structures are affected significantly by numerous material properties, including concrete and reinforcement moduli of elasticity, concrete modulus of rupture, creep, and shrinkage. The purposes of this chapter are to: 1) briefly address how each of these material properties affects deflection; and 2) provide brief guidance on the most common expressions recommended by various ACI committees for estimation of these parameters during the design process. This chapter is not intended to provide a comprehensive review of all the material prop-