

# Enhanced Construction Productivity Through Workability

Wednesday, November 6, 2024



## Field Evaluation of the Tarantula Curve and the Box Test to Assess/Predict the Workability of Concrete Paving Mixtures



U.S. Department of Transportation  
**Federal Highway Administration**

Jagan M Gudimettla, P.E.  
FHWA / Brick & Byte, Inc

# Disclaimers



- Except for any statutes or regulations cited, the contents of this presentation do not have the force and effect of law and are not meant to bind the public in any way. This presentation is intended only to provide information to the public regarding existing requirements under the law or agency policies.
- FHWA is the source of all images in this presentation unless otherwise noted.



# FHWA Mobile Concrete Technology Center (MCTC)

## ➤ Technology Transfer to SHA's

- Field demos on active projects
- Equipment loan
- Training of staff
- Conferences and workshops
- Specification review and technical assistance



# FHWA Data Collection Efforts

- Data from 24 States (30 project mixes)

- 2011-2019

- Only Mainline Paving projects

- Workability Analysis

- Combined Aggregate Gradation

- Tarantula Curve – 2011


- Box Test – 2015-2019

- Finish in the Field – 2015 - 2019

- Objectives


- Where do current gradations fall?

- Is there a correlation between Tarantula, Box Test and field observations?




# The Tarantula Curve

## ➤ Combined Aggregate Gradation



- Criterion 3
- Criterion 2
- Criterion 1




# Tarantula Curve

## ➤ 30 Mixtures

Tarantula Curve	Met	Did not Meet
Criterion 1	21	9

### Tarantula Curve: Criterion 1







# Tarantula Curve

➤ 30 Mixtures

Tarantula Curve	Met	Did not Meet
Criterion 2	29	1
Criterion 3	20	10



Tarantula Curve:  
Criterion 2



Tarantula Curve:  
Criterion 3

# The Box Test



- A workability test
- Simple
- Best use is for mixture design
- Will it go through the paver?







# Box Test

## ➤ Indicators


- Consolidation Ranking
- Edge Slump Potential




4



3




2




1

---

Consolidation Issues



Bottom Edge  
Slumping



Top Edge  
Slumping

If deflection is more than 1/4" then it fails


---

Edge Slump Issues

# Box Test Results



- Consolidation Ranking from Box Test
- Box Test Ranking from 19 Projects

Box Test Ranking Over 1.5	7 out of 19 projects
---------------------------	----------------------



# Tarantula Curve


## ➤ Project 16





# Box Test Results


## ➤ Project 16





# Field Performance



## ➤ Project 16





# Project 16



- Two Coarse and two fine aggregates
  - Flat and Elongated (Coarse)
  - Coarse Fine Aggregates





# Tarantula Curve

## ➤ Project 27



# Box Test Results

## ➤ Project 27





# Field Performance

## ➤ Project 27







# Tarantula Curve

## ➤ Project 17



## ➤ Edge Slump Issue



# Box Test Results and Field Performance

## ➤ Project 17



## ➤ Edge Slump



# Tarantula Curve

➤ Project 30

➤ Iowa






# Box Test Results

➤ Project 30

➤ Iowa



# Field Performance



## ➤ Project 30

## ➤ Iowa



# Tarantula Curve

- Project 31
- Minnesota






# Box Test Results



➤ Project 31

➤ Minnesota





# Field Performance

- Project 31
- Minnesota



# Tarantula Curve

- Project 26
- Arkansas






# Field Performance

➤ Project 26


➤ Arkansas



# Box Test Results

## ➤ Project 35

## ➤ Kansas






# Field Performance

## ➤ Project 35

## ➤ Kansas





# Assessing Change in Workability with Time

## Project A



0 min



15 min



30 min



45 min



60 min

## Project B



0 min



15 min



30 min



45 min



60 min



# Field Observations



**Project A**



**Project B**

# Observations



## ➤ Tarantula Curve

### ➤ Criterion 1 (individual sizes)

- Met most of the time
- One size aggregate is often off

### ➤ Criterion 2 (Coarse part of the fine aggregate)

- Almost always passes

### ➤ Criterion 3 (Fine part of the fine aggregate)

- Impacts consolidation and finishability
- Criterion is not met all the time



# Observations



- The Tarantula Curve, Box Test, and Field Observations Correlate in almost all cases
- The Box Test surface finish has excellent correlation to field finish
- Assess change in workability over time by running the Box Test at different intervals of time

**The Box Test is a great tool to use  
during the Mixture Design Process**



# THANK YOU!



**Jagan Gudimettla**

[Jagan.gudimettla.ctr@dot.gov](mailto:Jagan.gudimettla.ctr@dot.gov)

<https://www.fhwa.dot.gov/mctc>

